

Durability of Micropiles

Austrian Standardization Committee

Overview

General project descripitopn

Standards

Scope of application

Definitions

Design + execution

Control and monitoring

Standards

- EN 1997 and B1997-1-1 Geotechnical design general rules
- B 1997-1-3 Geotechnical design pile foundation
- EN 445 + 446 + 447 Grout for prestressing tendons
- EN 1990-1 Basis of structural design
- EN 14199 Execution of special geotechnical works Micropiles
- EN ISO 1461 Hot dip galvanized coatings on fabricated iron and steel articles – Specification and test methods
- RVS 13.03.21 Quality Control structural maintenance Monitoring, control and testing – anchored retaining structures

Definitions

- Anchorage system supplier
- Special construction management
- Special construction supervision
- Standard corrosion protection
- Double corrosion protection
- Durability
- Semi permanent anchorage
- Permanent anchorage

Design, Execution, control and monitoring

- Design
 - Exact definition of anchoring element anchor, nail, micropile
 - Partial safety factors, design model, resistance, checking load...
 - Environmental conditions
 - Measuring system and number of devices, checks depending on damage effects classification
- General requirements of micropiles + special requirements of corrosion protection
 - Usage of complete anchorage system
 - Assessment of soil concerning corrosivity
 - Corrosion protection depending on damage effect classification

Relation of planned period of usage and damage effect classification

Damage effect classification	Planned usage period in years			
	<u><</u> 2	<u><</u> 20	<u>≤</u> 50	<u>≤</u> 100
CC1	*	*	*	DCP
CC2	*	*	DCP	DCP
CC3	*	DCP	DCP	DCP

- Corrosion protection depending on soil properties either
 - Encapsulation with cement rout, concrete, mortar regrading crack width limitation
 - Sacrifical corrosion
 - Galvanizing of non drilled components
 - In addition tendons on non corroding material (GFK)

ISM Gold Coast 2019

6

Micropiles with alternating tensile-compression loading with planned usage period >20 years

- Encapsulation with, cement grout, mortar, concrete
- Sacrificial corrosion
- Galvanizing or coating
- Combination of above mentioned measures

Redundancy of construction – additional piles

Number of necessary	Demanded min. additional pile (tensile)			
piles	CC1	CC2	CC3	
1	1	1	1	
<u><</u> 4	≥1	≥1	<u>≥</u> 2	
>4 - <u><</u> 10	≥1	<u>≥</u> 2	<u>≥</u> 3	
>10	≥10% *	<u>≥</u> 20 *	≥30 *	

^{*} Percentage of piles correlated to necessary number of piles per structural element In design the failure of tensile pile taken into account, which causes the worst load case for the element Independently micropiles in an highly corrosive environment ust have DCP when used >7 years Hollow bar systems:

- Galvanizing is not a corrosion protection
- Encapsulation has to be executed under usage of spacers
- spacers must withstand drilling forces

Head construction of micropiles

- With alternating tensile-compression piles a tight connection to the corrosion protection has to be executes
- With alternating tensile-compression piles with SPC (sacrificial CP, galvanizing, coating) the upper part of minimum 1,50 m has to be protected by galvanizing all parts of the head
- In environment which disqualifies for galvanizing another protection method has to be chosen

Checking and control in considerable working height > 2,50 m

- Special design testing procedure
- In these cases testing without gauge stand possible while reading the displacement at the stressing jack
- Diplacement of support to be monitored

Additional quality assuring measures

- Specification of storing conditions on site by supplier
- Instruction concerning handling by the supplier for each project
- Instruction on site concernong all steps from unloading, storage, completion of corrosion protection by the system supplier

Tasks of supervisor

- Class CC2 and CC3 a supervisor has to be installed
- Experience with system is a must
- Participation in the instruction by system supplier is demanded
- Checking of design and testing
- Check of corrosion protection measures according to design
- Documentation of all relevant steps, tests and measures on site

Tasks of special construction manager

- Check of design and testing measures
- Experience with system is a must
- Participation in the instruction by system supplier is demanded
- Ensuring of adequate storage
- Check of all steps of installing
- Check of testing results
- Documentation of all relevant steps, tests and measures on site

Control of existing anchored structures

- Classification of tendons designed and installed according to previous standards or retracted standards according to EN 1997-1
- Permanent monitoring, control and testing according to RVS 13.03.21
- Micropiles must not be tested like anchors

Questions?

Thank You for your attention



IB BRANDNER

DIPL.-ING. ANDREAS BRANDNER



CHARTERED ENGINEERING CONSULTANT
AND MEDIATOR IN CIVIL ENGINEERING
A-6020 INNSBRUCK, KARL-SCHÖNHERR-STRASSE 8
WWW.IB-BRANDNER.COM | OFFICE@IB-BRANDNER.COM
TEL. +43 (0)512 56 33 32 | FAX +43 (0)512 56 33 324
M0BILE +43 (0)664 54 35 119